



DESCRIPTION

RestoFinish Polyprimer is a two component Polyester resin based Sealer Surfacer Primer. It is designed as an all inclusive coating for the use on a variety of substrates. Once sanded, it may be overcoated with a number of primers and topcoats.




SURFACE PREPARATION

Surface must be clean, dry and free of oil, grease, wax, rust, dirt or any foreign matter. Use appropriate cleaning process for each substrate. Remove sanding debris with air blower and if required clean with Restofinish surface cleaner. Ensure surface is completely clean and dry before paint application.

Mild Steel: Apply to abraded surface to AS1627.4 or mechanically sand with 80 grit. **DO NOT USE WAX & GREASE REMOVER**
Fibreglass: Sand with abrasive, minimum of 120 grit. Clean with RestoFinish Polyester Solvent before application.

Existing Finishers and Fillers: Ensure coatings are cured and dry. Sand with minimum 120-180 grit and ensure surface is free from dust.




MIXING

Mixing ratio is 100:2 by volume. This is equal to 2%.

Product	Volume	Weight
Polyprimer	1000mls	1330 grams
Polyprimer Hardener	20mls	20 grams

Can be reduced up to 10% with RestoFinish Polyester Solvent. Stir before use.



POT LIFE

Catalysed Polyprimer 20°C is one hour.

Use within temperature range 20°C - 30°C with humidity below 80%.

Cool temperatures and high relative humidity can affect the drying.



APPLICATION

Apply 1 medium coat, allow 10-30 minutes between coats.

Minimum 2 coats. Maximum 4 coats.

One coat is equal to 75-100 microns.



GUN SETUP AND CLEANING


Fluid tip 1.8 - 2.0mm @ 25-35 PSI.

Clean equipment with RestoFinish Polyprimer Solvent or Acetone.



FINISHING

For best results allow 24 hours cure above 20°C. Dry sand to desired finish. Remove sanding debris with air blower and if required clean with Restofinish surface cleaner. Ensure surface is completely clean and dry before paint application.



STORAGE / SHELF LIFE

Maximum 1 year under normal storage conditions

10°C - 30°C unopened container.

Avoid direct sunlight.

HEALTH AND SAFETY FOR PROFESSIONAL USE ONLY. Full instructions must be read before use. Please refer to RestoFinish Polyprimer – Part A Safety Data Sheets (SDS) and product labels for full Health and Safety details and product handling instructions. **IMPORTANT:** This product contains hazardous materials and appropriate PPE (personal protective equipment) must always be used.

Products are suitable for professional use only. The data on this sheet indicate typical values. As application variables are a major factor in product performance, this information should serve as a general guide only. The data included in this application are based on our present knowledge and experience. RestoFinish assumes no responsibility or liability for use of this information. UNLESS RESTOFINISH AGREES IN WRITING, RESTOFINISH ASSUMES NO WARRANTIES, EXPRESS OR IMPLIED, AND REPUDIATES ALL IMPLIED WARRANTIES INCLUDING WARRANTIES OF MERCHANTABILITY OR SUITABILITY FOR A PARTICULAR USE OR FREEDOM FROM PATENT INFRINGEMENT. RESTOFINISH WILL NOT BE LIABLE FOR ANY INCIDENTAL, SPECIAL OR SIGNIFICANT DAMAGES. Your only remedy for any fault in this product is the replacement of the defective product, or a refund of the product purchase price, at our discretion. The latest version supersedes all preceding versions. You can obtain the most recent version from our website www.restofinish.com.au or directly from your sales agent. It is the responsibility of the beneficiary of our products to verify that any proprietary rights and existing laws and legislation are observed. RestoFinish© (a division of Global Finish Pty Ltd). All rights reserved. v0922

IN AN EMERGENCY DIAL 000 (AUS) or 111 (NZ) POLICE OR FIRE BRIGADE

RESTOFINISH A Division of Global Finish Pty Ltd 6/8 Stockyard Place, West Gosford NSW Australia 2250

Telephone: + 61 (2) 4321 0339 Facsimile: + 61 (2) 4321 0338 Email: info@restofinish.com.au www.restofinish.com.au