

# **MAXILIGHT**

**A21** 

VERSION: 121212 Page: 1/2

# **BODYFILLER**

# **DEFINITION**

Lightweight polyester bodyfiller. Formulated for fast work, dries rapidly and is easy to sand. Its creamy texture and good spreading allows easy repair of large areas. This is the reason why this putty is produced in larger packaging.

#### PHYSICAL CHARACTERISTICS

Nature: Unsaturated polyester

Colour: Grey

Specific weight: 1,1 kg/l at 20°C

**VOC:** 25 g/l Mixing Application

#### **AUXILIARY PRODUCTS**

Hardener PBO

#### **SUITABLE SURFACES**

It may be applied on steel, electrozinc-coated, galvanised, aluminium or polyester surfaces. When maximum protection is required apply on epoxy primer.

Do not apply on thermoplastic finishes and Wash Primers.

# **SURFACE PREPARATION**

- 1 Identify surface.
- 2 Process:

PROCESS	_	1	Steel	Aluminium	Electrozinc- coated	Polyester UP-GFK
	P80		<b>√</b>	<b>√</b>	<b>√</b>	<b>√</b>
	P150		1	4	7	7
	DA93		1	٧	٧	1



VERSION: 121212 Page: 2/2

#### 1 - APPLICATION

	A : B WEIGHT	2 +	$\left(\begin{array}{c} \\ \\ \end{array}\right)$
10°C		9'	30'
20°C	100:2-3	7'	20'
30°C		4,5'	15'

TIME
5 min
DISTANCE
80 cm
MAX. T
80°C

2 - SANDING

		ORBIT		
		7 – 5 mm	P120	P100
INITIAL				P180
FINAL	<b> </b>	5 – 3 mm	P220	P240

# **REMARKS**

Do not add more hardener than specified. Mix thoroughly. It must be isolated before applying finish coating. Polyester putties will not harden at temperatures under +5°C.

# **EQUIPMENT CLEANING**

Clean putty knifes with a cleaning thinner before the product hardens.

# **SAFETY**

Follow instructions of product label. For more information check the Safety Data Sheet. Compliant with the National Statutory Regulation for Health and Safety at Work and Waste Disposal.

#### **STORAGE**

Store the product in a ventilated place far from direct exposure to sunlight. Keep between +5°C and +30°C.

#### **GUARANTEE**

In unopened original packaging, one year from manufacturing date.

# **SUGGESTION:**

Use a putty knife adapted to the surface to be repaired.
The putty knife choice will be done according to its size and shape.

For any technical information contact with our Customer Attention Service or our Technical Department.

ROBERLO SA declines any responsibility due to an incorrect use of the product.